

Product information

Rearview Mirror Adhesive Set

PI 6/21/04/2015



Description

Liqui Moly Rearview Mirror Adhesive Set consists of a high-strength anaerobic adhesive with an impregnated nylon grid which is used both as a support for retention and as a catalyst for the adhesive. Liqui Moly Rearview Mirror Adhesive Set has been specially developed for bonding the feet of rearview mirrors to windshields as well as the hinges on hinged side windows. Due to its high viscosity, the Liqui Moly Rearview Mirror Adhesive Set can also be used on vertical surfaces. Liqui Moly Rearview Mirror Adhesive Set compensates excellently for different thermal expansions and can therefore be safely used for bonding all types of rearview mirror feet to windshields. **Also suitable for Ford and Seat models.** This adhesive set can also be used in the furniture industry for bonding metals or plastics to glass surfaces.

Properties

- high shear stability
- rapid curing
- outstanding compensation for different thermal expansions
- outstanding bond strength
- suitable for bonding all types of rear-view mirror feet

Technical data

| | |
|---------------------------------|--|
| Form | flüssig / liquid |
| Recommended storage temperature | 5 - 25 °C |
| Base | anaerober Klebstoff Imprägniertes Nylon-Gitternetz / anaerobic adhesive |
| Color / appearance | transparent |
| Working strength | 15 min |
| Flash point | > 100 °C |
| Odor | charakteristisch / characteristic |
| Shelf life | 24 Monate |
| Solubility in water | unlöslich / insoluble |
| Full curing | 2 min |
| Optimum storage temperature | +5 °C bis +25 °C / +5 °C to +25 °C |
| Density at 20 °C | 1,08 g/cm ³ |



Areas of application

Liqui Moly Rückspiegel-Klebe-Set wird im Fahrzeugbau eingesetzt um Rückspiegelfüße an der Windschutzscheibe zu befestigen sowie zum Verkleben von Scharnieren an Ausstell-Seitenfenstern u.s.w. Des Weiteren kann Liqui Moly Rückspiegel-Klebe-Set in der Möbelindustrie zur Verklebung von Metall oder Kunststoffen auf Glasoberflächen verwendet werden.

Application

The bonding surfaces must be dry and free of dirt, grease and oil residues. For cleaning, we recommend Liqui Moly Cleaner and Thinner Part no. 6130. The impregnated nylon grid is used as a bonding agent and should be trimmed to the size of the area to be bonded. Next, hold the component to be bonded on the surface of the glass and mark the desired position. Apply the adhesive to the component to be bonded and place the grid on top. Next, hold the component to be bonded onto the surface of the glass and press under low pressure for about 2 minutes. After a curing time of approx. 15 minutes, the adhesive will have reached working strength and the mirror can be mounted on the mirror foot.

Available pack sizes

| | |
|--------------|-------------------------|
| 1 ml Blister | 6194 D-GB-F-I-E-NL-P |
| 1 ml Blister | 8059 D-RUS-UA |

Our information is based on thorough research and may be considered reliable, although not legally binding.